

WEIBULL AD

Modified Mimosa Extract

WEIBULL AD is a high astringency and high concentration acid Mimosa extract. Its use is recommended in leather vegetable tanning and retanning processes in general.

Properties

Because **WEIBULL AD** is a high astringency and high tannin content extract, it provides excellent filling and fibre compaction to tanned and retanned leathers alike. Its great affinity with fibres provides strong fixation of tannins to pelts, thus resulting in good yield in tanning. In retanning, the action of **WEIBULL AD** improves leather buffing and embossing operations. It is recommended to use this product as supplementary tannin both on sole leather and vegetable tanned kipskin. **WEIBULL AD** is soluble in water.

Typical Analysis

Physical aspect: Hygroscopic, dust-free, dark brown powder

Ionic character: Anionic

PCP: Free

Active matter (%): 93.5 - Minimum

pH (Aqueous Sol. 20% w/v): 3.0 - 3.6

Application

WEIBULL AD may be used either on its own or in combination with other vegetable, synthetic and/or auxiliary extracts.

It is recommended to use **WEIBULL AD** as follows:

In vegetable tanning:

Vachetta: 25 - 30% calculated on the weight of the limed pelts

Belt leather: 35 - 40% calculated on the weight of the limed pelts

Heel cover leather: 38 - 42% calculated on the weight of the limed pelts

Sole leather: 45 - 50% calculated on the weight of the limed pelts

In retanning:

Semi-chrome: 8 - 14% calculated on the weight of the shaved pelts

High Veg: 15 - 25% calculated on the weight of the shaved pelts

Nobuck: 5 - 10% calculated on the weight of the shaved pelts

Storage

WEIBULL AD must be stored in tightly closed packaging in a clean, dry, aired place protected from sunlight for a period not exceeding twelve (12) months.

Presentation

WEIBULL AD is available in powder form, packed in 25 kg bags (net weight). It may also be supplied in bulk or pallets.

Toxicological Information

Please refer to the relevant **MSDS** (Material Safety Data Sheet) which may be found in our website. Alternatively, please contact our Sales Department.

For further information please contact our **Technical Department**:

Telephone: **(+55 51) 3632.4055**

Fax: **(+55 51) 3632.2499**

e-mail: **export@tanac.com.br**

web page: **www.tanac.com.br**

The present information and our technical advice are provided in good faith and do not constitute a formal warranty. This also applies when the rights of third parties are involved. The information is therefore given as a mere indication and does not relieve users of our products from the obligation to check its validity and/or test our products in an adequate manner for the processes and uses they are intended for.

Review: AH0109