

# WEIBULL L

## Light-coloured Mimosa Extract

**WEIBULL L** is a light-coloured, low astringency Mimosa vegetable extract, processed from selected raw materials.

### Properties

The low astringency and low viscosity of **WEIBULL L** provide fine grain, good penetration, smoothness and homogeneous dyeing to tanned and retanned leathers alike. **WEIBULL L** is soluble in water.

### Typical Analysis

Physical aspect: Beige, hygroscopic and dust-free powder

Ionic character: Anionic

PCP: Free

Tannin content (%):  $68.0 \pm 2.0$

( $72.0 \pm 2.0$  Dry basis)

pH (Aqueous Sol. 20% w/v): 4.0 - 5.0

Colour\*\* Red: 0.8 - 1.0

Yellow: 1.7 - 2.0

\* Filter Method: analytical solution containing 0.4% w/v of pure tannin.

Higher tanning agent values than those mentioned above are acceptable.

\*\* Colour Standard Test: Lovibond Colorimeter - 1cm<sup>3</sup> cell - analytical solution containing 0.4% w/v of pure tannin.

### Application

**WEIBULL L** may be used either on its own or in combination with other vegetable, synthetic and/or auxiliary extracts.

It is recommended to use **WEIBULL L** as follows:

#### In vegetable tanning

**Vachetta:** 25 - 30% calculated on the weight of the limed pelts

**Belt leather:** 35 - 40% calculated on the weight of the limed pelts

#### In retanning

**Nappa:** 4 - 8% calculated on the weight of the shaved pelts

**Semi-chrome:** 8 - 14% calculated on the weight of the shaved pelts

**High Veg:** 15 - 25% calculated on the weight of the shaved pelts

### **Storage**

**WEIBULL L** must be stored in tightly closed packaging in a clean, dry, aired place protected from sunlight for a period not exceeding twelve (12) months.

### **Presentation**

**WEIBULL L** is available in powder form, packed in 25 kg bags (net weight). It may also be supplied in bulk or pallets.

### **Toxicological Information**

Please refer to the relevant **MSDS** (Material Safety Data Sheet) which may be found in our website. Alternatively, please contact our Sales Department.

For further information please contact our **Technical Department:**

Telephone: **(+55 51) 3632.4055**

Fax: **(+55 51) 3632.2499**

e-mail: **export@tanac.com.br**

web page: **www.tanac.com.br**

The present information and our technical advice are provided in good faith and do not constitute a formal warranty. This also applies when the rights of third parties are involved. The information is therefore given as a mere indication and does not relieve users of our products from the obligation to check its validity and/or test our products in an adequate manner for the processes and uses they are intended for.

Review: A00109